

**In The Specification**

Page 4, please replace the paragraph bridging pages 4 and 5 with the following:

-- In the body portion 11 of the leno weave, it should be noted that warp threads B of polyurethane double covered yarn and warp threads C of polyurethane bare yarn are interlaced with weft threads A to provide a roughened or irregular surface on the fabric tape 1 that serves to resist slippage. In a preferred embodiment of the present invention, the antislip fabric is woven by interlacing weak tensioned warp threads B of polyurethane double covered yarn and somewhat loose warp threads C of polyurethane bare yarn with each other to provide a plurality of spaced-apart nubs 111 of the loose polyurethane bare yarn formed on the polyurethane double covered yarn. As described above, the spaced-apart nubs 111 are formed of the polyurethane bare yarn which has a high frictional resistance. Accordingly, the antislip fabric according to the invention has a frictional surface with a higher frictional resistance than conventional antislip tapes comprising a rubber braid sewn into a cloth tape. The two opposed edge portions 12 of the antislip strip 1 are woven in the form of plain weave by using polyester monofilament as weft threads and polyester filament and woolie polyester as warp threads. As can be seen from Fig. 2, the nubs 111 are directed obliquely to the longitudinal direction of the fabric. It should also be noted that at each end the nubs 111 are joined to a part of its corresponding thread C which are directed in a parallel direction to the direction of the fabric. --